



EZPRENE® 9585A SHF

ENPLAST Americas, a Ravago Group Company - Thermoplastic Vulcanizate

Wednesday, November 6, 2019

General Information

Product Description

85 Shore A TPE (Thermoplastic Vulcanizate). Available in black, natural for injection molding applications with long flow lengths or requires highly cosmetic surface. This soft, easy to color material is non-hygroscopic and offers excellent chemical resistance and physical properties. EZPrene 9500 series materials are polyolefin based and 100% recyclable.

General

Material Status	• Commercial: Active		
Availability	• North America		
Features	• Chemical Resistant	• Good Colorability	• Recyclable Material
	• Fatigue Resistant	• Low to No Water Absorption	• Soft
	• Good Adhesion	• Ozone Resistant	• UV Resistant
Appearance	• Black	• Natural Color	
Processing Method	• Extrusion	• Injection Molding	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.942		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	247	psi	ASTM D412
Tensile Strength (Break)	754	psi	ASTM D412
Tensile Elongation (Break)	490	%	ASTM D412
Tear Strength	65.7	lbf/in	ASTM D624
Compression Set			ASTM D395
73°F, 22 hr	45	%	
257°F, 70 hr	72	%	
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shore A, 5 sec, Extruded	84		
Shore A, 5 sec, Injection Molded	88		
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-85.0	°F	ASTM D746
Dynamic Service Temperature	266	°F	
Additional Information	Nominal Value	Unit	Test Method
Ozone Resistance	Excellent		ASTM D1149

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	375 to 400	°F
Middle Temperature	385 to 410	°F
Front Temperature	385 to 410	°F
Nozzle Temperature	410 to 430	°F
Processing (Melt) Temp	390 to 430	°F
Mold Temperature	75 to 125	°F

EZPRENE® 9585A SHF

ENPLAST Americas, a Ravago Group Company - Thermoplastic Vulcanizate

Injection	Nominal Value	Unit
Injection Pressure	750 to 1300	psi
Injection Rate	Fast	
Screw Speed	50 to 200	rpm
Clamp Tonnage	2.0 to 3.5	tons/in ²
Cushion	0.200 to 0.500	in

Injection Notes

Holding Time: 5 to 7 Sec.
Cooling Time: 30 to 50 Sec.

Extrusion	Nominal Value	Unit
Hopper Temperature	330 to 350	°F
Cylinder Zone 1 Temp.	340 to 375	°F
Cylinder Zone 2 Temp.	340 to 375	°F
Cylinder Zone 3 Temp.	340 to 375	°F
Cylinder Zone 4 Temp.	340 to 375	°F
Cylinder Zone 5 Temp.	340 to 375	°F
Adapter Temperature	375 to 410	°F
Melt Temperature	375 to 390	°F
Die Temperature	375 to 410	°F
Screw L/D Ratio	24.0:1.0	

Extrusion Notes

Compression Zone: 355 - 390°F (180 - 200°C)
Metering Zone: 375 to 410°F (190 to 210°C)
Screw Speed: 30 - 80 rpm
Screen Pack: 20/40/60

Notes

¹ Typical properties: these are not to be construed as specifications.