



Elvaloy® HP662

DuPont Packaging & Industrial Polymers - Thermoplastic

Wednesday, November 6, 2019

General Information

Product Description

DuPont™ Elvaloy® HP662 is a ethylene terpolymer, which is most commonly used as a modifier for a variety of other polymers.

E/nBA/CO = ethylene/n-butyl acrylate/carbon monoxide

General

Material Status	• Commercial: Active	
Availability	• Europe	• North America
Uses	• Plastics Modification	
Forms	• Pellets	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.962		ASTM D792
Density	0.960	g/cm ³	ISO 1183
Melt Mass-Flow Rate (190°C/2.16 kg)	25	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	25	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	493	psi	ASTM D638
Tensile Stress (Break)	493	psi	ISO 527-2
Tensile Elongation (Break)	1100	%	ASTM D638
Tensile Strain (Break)	1100	%	ISO 527-2
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	69		ASTM D2240
Shore Hardness (Shore A)	69		ISO 868
Thermal	Nominal Value	Unit	Test Method
Glass Transition Temperature ²	-65.2	°F	ASTM E1356
Peak Melting Temperature	144	°F	ASTM D3418
Melting Temperature (DSC)	144	°F	ISO 3146

Notes

¹ Typical properties: these are not to be construed as specifications.

² loss modulus peak at 1 hz