



Estane® ZHF 58370 NAT 01 EXP

Lubrizol Advanced Materials, Inc. - Thermoplastic Polyurethane Elastomer (Polyether)

Wednesday, November 6, 2019

General Information

Product Description

Type: ESTANE® ZHF 58370 NAT 01 EXP is a non-halogen, flame retardant, aromatic polyether-based thermoplastic polyurethane.

Application: Extrusion

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Aromatic	• Flame Retardant	• Halogen Free
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Extrusion		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 2781
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/5A/200
--	4500	psi	
50% Strain	725	psi	
100% Strain	870	psi	
300% Strain	1310	psi	
Tensile Strain (Break)	650	%	ISO 527-2/5A/200
Abrasion Resistance	91.0	mm ³	ISO 4649-A
Elastomers	Nominal Value	Unit	Test Method
Tear Strength ²	280	lbf/in	ISO 34-1
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 1 sec)	86		ISO 868
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.08 in)	V-2		UL 94
Oxygen Index	23	%	ASTM D2863

Processing Information

Extrusion	Nominal Value	Unit
Drying Temperature	212	°F
Drying Time	3.0 to 4.0	hr
Cylinder Zone 1 Temp.	356	°F
Cylinder Zone 2 Temp.	365	°F
Cylinder Zone 3 Temp.	374	°F
Cylinder Zone 4 Temp.	365	°F
Adapter Temperature	365	°F
Die Temperature	356	°F

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Estane® ZHF 58370 NAT 01 EXP

Lubrizol Advanced Materials, Inc. - Thermoplastic Polyurethane Elastomer (Polyether)

Notes

¹ Typical properties: these are not to be construed as specifications.

² Method Bb, Angle (Nicked)