



## Formolene® 1102K

Formosa Plastics Corporation, U.S.A. - High Crystallinity Polypropylene

Tuesday, November 5, 2019

### General Information

#### Product Description

Formolene® 1102K is a high molecular weight, homopolymer polypropylene designed for extrusion processes, notably biaxially oriented film (BOPP). It contains a unique combination of stabilizers, which provides excellent processability and good end use performance. It does not contain slip or antiblock.

Formolene® 1102K meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact.

#### General

Material Status	• Commercial: Active		
Availability	• North America		
Additive	• Processing Aid		
Features	• Food Contact Acceptable	• High Molecular Weight	• No Animal Derived Components
	• Good Processability	• Homopolymer	
Uses	• Bi-axially Oriented Film		
Agency Ratings	• EC 1907/2006 (REACH)	• FDA 21 CFR 177.1520	
Forms	• Pellets		
Processing Method	• Film Extrusion		

### ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (230°C/2.16 kg)	3.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup> (Yield, Injection Molded)	4930	psi	ASTM D638
Tensile Elongation <sup>2</sup> (Yield, Injection Molded)	10	%	ASTM D638
Flexural Modulus - 1% Secant <sup>3</sup> (Injection Molded)	200000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, Injection Molded)	1.0	ft·lb/in	ASTM D256A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, Injection Molded)	105		ASTM D785

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 2.0 in/min

<sup>3</sup> 0.051 in/min