



Fortron® 9115L0

Celanese Corporation - Polyphenylene Sulfide

Tuesday, November 5, 2019

General Information

Product Description

Fortron® 9115L0 is a 15% fiberglass-reinforced grade of polyphenylene sulfide with high melt strength suitable for blow molding and extrusion applications.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
Filler / Reinforcement	• Asia Pacific • Latin America		
Features	• Glass Fiber, 15% Filler by Weight		
Processing Method	• High Melt Strength	• Blow Molding	• Extrusion

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.44	g/cm ³	ISO 1183
Water Absorption (Saturation, 73°F)	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.12E+6	psi	ISO 527-2/1A
Tensile Stress (Break)	17400	psi	ISO 527-2/1A/5
Tensile Strain (Break)	2.0	%	ISO 527-2/1A/5
Flexural Modulus (73°F)	1.09E+6	psi	ISO 178
Flexural Stress (73°F)	29000	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.4	ft·lb/in ²	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	15	ft·lb/in ²	ISO 179/1eU
Notched Izod Impact Strength (73°F)	2.5	ft·lb/in ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	428	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	239	°F	ISO 75-2/C
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.030 in)	V-0		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	266 to 284	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.020	%
Hopper Temperature	68 to 86	°F
Rear Temperature	554 to 572	°F
Middle Temperature	590 to 608	°F
Front Temperature	626 to 644	°F
Nozzle Temperature	590 to 626	°F

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Fortron® 9115L0

Celanese Corporation - Polyphenylene Sulfide

Injection	Nominal Value	Unit
Processing (Melt) Temp	626 to 644	°F
Mold Temperature	284 to 320	°F
Injection Rate	Fast	
Back Pressure	< 435	psi

Injection Notes

Feeding zone temperature: 60 to 80°C

Zone4 temperature: 330 to 340°C

Hot runner temperature: 330 to 340°C

Notes

¹ Typical properties: these are not to be construed as specifications.