



## HYPRO® PP-CP 20/10

Entec Polymers - Polypropylene Impact Copolymer

Tuesday, November 5, 2019

### General Information

#### Product Description

This product is intended for general purpose injection molding applications including flooring, automotive, appliance, lawn & garden and industrial application.

#### General

Material Status	• Commercial: Active
Availability	• North America
Features	• General Purpose • Impact Copolymer
Uses	• Appliances • Flooring • Industrial Applications • Automotive Applications • General Purpose • Lawn and Garden Equipment
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

### ASTM & ISO Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm <sup>3</sup>	ASTM D1505
Melt Mass-Flow Rate (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.013	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 73°F)	3480	psi	ASTM D638
Tensile Elongation (Yield, 73°F)	6.0	%	ASTM D638
Flexural Modulus - 1% Secant <sup>2</sup> (73°F)	175000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	> 10	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	221	°F	ASTM D648

### Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 420	°F
Middle Temperature	380 to 460	°F
Front Temperature	400 to 480	°F
Nozzle Temperature	380 to 460	°F
Processing (Melt) Temp	400 to 480	°F
Mold Temperature	70 to 120	°F
Injection Pressure	500 to 1500	psi

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.051 in/min