



HYPRO® PP-HP 35NS

Entec Polymers - Polypropylene Homopolymer

Tuesday, November 5, 2019

General Information

Product Description

This product is intended for thin-wall injection molding applications such as caps & closures, food containers and consumer products that require high stiffness.

General

Material Status	• Commercial: Active	
Availability	• North America	
Additive	• Antistatic	• Nucleating Agent
Features	• Antistatic • High Stiffness	• Homopolymer • Nucleated
Uses	• Caps • Closures	• Consumer Applications • Food Containers
RoHS Compliance	• RoHS Compliant	
Forms	• Pellets	

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (230°C/2.16 kg)	35	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.013	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 73°F)	5700	psi	ASTM D638
Tensile Elongation (Yield, 73°F)	8.0	%	ASTM D638
Flexural Modulus - 1% Secant ² (73°F)	250000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.60	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	261	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Rear Temperature	360 to 420	°F
Middle Temperature	380 to 460	°F
Front Temperature	400 to 480	°F
Nozzle Temperature	380 to 460	°F
Processing (Melt) Temp	400 to 480	°F
Mold Temperature	70 to 120	°F
Injection Pressure	500 to 1500	psi

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.051 in/min

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.