



HYPRO-F® PPH-CC20 NATURAL

Entec Polymers - Polypropylene Homopolymer

Tuesday, November 5, 2019

General Information

Product Description

Homopolymer Polypropylene, 20% Calcium Carbonate Filled, 10 Melt Flow

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Calcium Carbonate, 20% Filler by Weight
Features	• Copolymer
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Pellets

ASTM & ISO Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.05		ASTM D792
Melt Mass-Flow Rate (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Mechanical			
Tensile Strength (Yield, 73°F)	4100	psi	ASTM D638
Tensile Elongation (Yield, 73°F)	7.0	%	ASTM D638
Tensile Elongation (Break, 73°F)	30	%	ASTM D638
Flexural Modulus - Tangent (73°F)	270000	psi	ASTM D790
Flexural Strength (73°F)	5500	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	0.75	ft·lb/in	ASTM D256
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	210	°F	ASTM D648

Notes

¹ Typical properties: these are not to be construed as specifications.