



Hostaform® C 9021 GV1/10

Celanese Corporation - Acetal (POM) Copolymer

Saturday, November 2, 2019

General Information

Product Description

Chemical abbreviation according to ISO 1043-1: POM Molding compound ISO 9988- POM-K, M-GNR, 02-003, GF10 POM copolymer Injection molding type, reinforced with ca. 10 % glass fibers; high resistance to thermal and oxidative degradation; reduced thermal expansion and shrinkage. UL-registration in natural and black and a thickness more than 1.5 mm as UL 94 HB, temperature index UL 746 B, electrical 105 °C, mechanical 105 °C Burning rate ISO 3795 and FMVSS 302 < 100 mm/min for a thickness more than 1 mm. Ranges of applications: For molded parts with high strength and rigidity as well as higher hardness. FMVSS = Federal Motor Vehicle Safety Standard (USA) UL = Underwriters Laboratories (USA)

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
Filler / Reinforcement	• Asia Pacific		
Features	• Glass Fiber, 10% Filler by Weight	• High Strength	• Low Shrinkage
RoHS Compliance	• High Hardness		
Processing Method	• Contact Manufacturer	• High Stiffness	• Low Shrinkage
Resin ID (ISO 1043)	• Injection Molding		
	• POM		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	6.00	cm ³ /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	1.1	%	
Flow	1.4	%	
Water Absorption (Saturation, 73°F)	0.85	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.19	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	696000	psi	ISO 527-2/1A
Tensile Stress (Break)	13100	psi	ISO 527-2/1A/5
Tensile Strain (Break)	4.0	%	ISO 527-2/1A/5
Tensile Creep Modulus (1 hr)	537000	psi	ISO 899-1
Tensile Creep Modulus (1000 hr)	363000	psi	ISO 899-1
Flexural Modulus (73°F)	653000	psi	ISO 178
Flexural Stress	18900	psi	ISO 178
Flexural Strain at Break	3.4	%	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	3.1	ft·lb/in ²	
73°F	3.1	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	24	ft·lb/in ²	
73°F	19	ft·lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness ²	24700	psi	ISO 2039-1

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Hostaform® C 9021 GV1/10

Celanese Corporation - Acetal (POM) Copolymer

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	309	°F	ISO 75-2/A
Heat Deflection Temperature (1160 psi, Unannealed)	147	°F	ISO 75-2/C
Vicat Softening Temperature	313	°F	ISO 306/B50
Melting Temperature ³	331	°F	ISO 11357-3
CLTE - Flow	4.4E-5	in/in/°F	ISO 11359-2
CLTE - Transverse	5.0E-5	in/in/°F	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Electric Strength	890	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
100 Hz	4.10		
1 MHz	4.10		
Dissipation Factor			IEC 60250
100 Hz	3.0E-3		
1 MHz	6.0E-3		
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	HB		
0.12 in	HB		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	212 to 248	°F
Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	0.15	%
Hopper Temperature	68 to 86	°F
Rear Temperature	338 to 356	°F
Middle Temperature	356 to 374	°F
Front Temperature	374 to 392	°F
Nozzle Temperature	374 to 410	°F
Processing (Melt) Temp	374 to 410	°F
Mold Temperature	176 to 248	°F
Injection Rate	Slow	
Back Pressure	< 290	psi

Injection Notes

Feeding zone temperature: 60 to 80°C

Zone4 temperature: 190 to 210°C

Hot runner temperature: 190 to 210°C

Notes

¹ Typical properties: these are not to be construed as specifications.

² 30s

³ 10°C/min