



INEOS PP H13M-00

INEOS Olefins & Polymers USA - Polypropylene Homopolymer

Tuesday, November 5, 2019

General Information

Product Description

H13M-00 is a medium-term heat aging polypropylene homopolymer designed for injection molding applications such as automotive parts, appliances and medical and rigid packaging. This grade benefits from a good retention of physical properties when exposed to higher in-service temperatures over an extended period of time, even following hot-water extraction. This material has been recognized by UL for sustained use at 100°C and meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520.

General

Material Status	• Commercial: Active	
Availability	• North America	
Features	• Food Contact Acceptable	• Homopolymer
Uses	• Appliances	• Medical Packaging
	• Automotive Applications	• Rigid Packaging
Agency Ratings	• EC 1907/2006 (REACH)	• FDA 21 CFR 177.1520
RoHS Compliance	• Contact Manufacturer	
Forms	• Pellets	
Processing Method	• Injection Molding	

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.913		ASTM D792
Melt Mass-Flow Rate (230°C/2.16 kg)	14	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	5360	psi	ASTM D638
Tensile Strength ² (Break)	2480	psi	ASTM D638
Tensile Elongation ² (Yield)	9.1	%	ASTM D638
Tensile Elongation ² (Break)	140	%	ASTM D638
Flexural Modulus - 1% Secant	240000	psi	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	0.60	ft·lb/in	ASTM D256
Notched Izod Impact (Area) (73°F)	1.48	ft·lb/in ²	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	105		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	221	°F	ASTM D648
RTI Elec (0.24 in)	212	°F	UL 746
RTI Imp (0.24 in)	212	°F	UL 746
RTI Str (0.24 in)	212	°F	UL 746
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.24 in)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Gloss (60°)	92		ASTM D2457
Haze ³ (50.0 mil)	76.0	%	ASTM D1003

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

INEOS PP H13M-00

INEOS Olefins & Polymers USA - Polypropylene Homopolymer

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min

³ 23°C