



INEOS PP N12Z-00

INEOS Olefins & Polymers USA - Polypropylene Impact Copolymer

Tuesday, November 5, 2019

General Information

Product Description

N12Z-00 is a medium melt flow rate, nucleated and antistatic polypropylene impact copolymer designed for injection molding applications. The grade benefits from a high stiffness, high impact resistance at room and low temperatures, excellent mold release, and good static dissipation. This material meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520.

General

Material Status	<ul style="list-style-type: none"> Commercial: Active 		
Availability	<ul style="list-style-type: none"> North America 		
Additive	<ul style="list-style-type: none"> Antistatic 	<ul style="list-style-type: none"> Nucleating Agent 	
Features	<ul style="list-style-type: none"> Antistatic Food Contact Acceptable Good Mold Release 	<ul style="list-style-type: none"> High Impact Resistance High Stiffness Impact Copolymer 	<ul style="list-style-type: none"> Low Temperature Impact Resistance Medium Flow Nucleated
Agency Ratings	<ul style="list-style-type: none"> EC 1907/2006 (REACH) 	<ul style="list-style-type: none"> FDA 21 CFR 177.1520 	
RoHS Compliance	<ul style="list-style-type: none"> Contact Manufacturer 		
Forms	<ul style="list-style-type: none"> Pellets 		
Processing Method	<ul style="list-style-type: none"> Injection Molding 		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.903		ASTM D792
Melt Mass-Flow Rate (230°C/2.16 kg)	12	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	3260	psi	ASTM D638
Tensile Strength ² (Break)	2610	psi	ASTM D638
Tensile Elongation ² (Yield)	6.6	%	ASTM D638
Tensile Elongation ² (Break)	380	%	ASTM D638
Flexural Modulus - 1% Secant	154000	psi	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (-4°F)	1.7	ft·lb/in	ASTM D256
Notched Izod Impact (Area)			ASTM D256
-4°F	4.24	ft·lb/in ²	
73°F	No Break		
Instrumented Impact, Ductility			ASTM D3763
-4°F	Ductile		
73°F	Ductile		
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	66		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	201	°F	ASTM D648
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed	127	°F	
Vicat Softening Temperature	291	°F	ASTM D1525

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

INEOS PP N12Z-00

INEOS Olefins & Polymers USA - Polypropylene Impact Copolymer

Optical	Nominal Value	Unit	Test Method
Gloss (60°)	68		ASTM D2457

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min