



KIBISAN® PN-127 L100 FG

CHI MEI CORPORATION - Styrene Acrylonitrile

Tuesday, November 5, 2019

General Information

Product Description

Food Contact SAN KIBISAN PN-127 L100 FG

Product Description: Injection molding

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
Features	• Asia Pacific • Food Contact Acceptable		
RoHS Compliance	• RoHS Compliant		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• >SAN<		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density (73°F)	1.06	g/cm ³	ISO 1183
Melt Volume-Flow Rate (MVR) (220°C/10.0 kg)	17	cm ³ /10min	ISO 1133
Molding Shrinkage	0.20 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	10700	psi	ISO 527-2/50
Tensile Stress (Break)	10700	psi	ISO 527-2/50
Tensile Strain (Break)	7.0	%	ISO 527-2/50
Flexural Modulus ²	479000	psi	ISO 178
Flexural Stress ²	15200	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	0.95	ft-lb/in ²	ISO 179
Notched Izod Impact Strength (73°F)	1.4	ft-lb/in ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	194	°F	ISO 75-2/A
Heat Deflection Temperature (264 psi, Annealed)	214	°F	ISO 75-2/A
Vicat Softening Temperature			
--	221	°F	ISO 306/A50
--	219	°F	ISO 306/B50
CLTE - Flow	2.0E-5 to 2.1E-5	in/in/°F	ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.