



Optix® CP-1000I

Plaskolite, Inc. - Polymethyl Methacrylate Acrylic

Sunday, November 3, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Features	• Chemical Resistant • Electrically Insulating • Good Dimensional Stability • Good Impact Resistance	• Good Processability • Good Weather Resistance • High Clarity • Low Flow	• Low Odor • Low to No Taste • Machinable
Automotive Specifications	• SAE J576		
Appearance	• Colors Available		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.16		ASTM D792
Melt Mass-Flow Rate (230°C/3.8 kg)	2.7	g/10 min	ASTM D1238
Molding Shrinkage - Flow	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	270000	psi	ASTM D638
Tensile Strength	6100	psi	ASTM D638
Tensile Elongation (Break)	37	%	ASTM D638
Flexural Modulus	260000	psi	ASTM D790
Flexural Strength	8900	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.2	ft-lb/in	ASTM D256
Unnotched Izod Impact	19	ft-lb/in	ASTM D256
Gardner Impact	52.0	in-lb	ASTM D3029
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	36		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	180	°F	ASTM D648
Vicat Softening Temperature	211	°F	ASTM D1525
CLTE - Flow (-22 to 86°F)	4.5E-5	in/in/°F	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Refractive Index	1.490		ASTM D542
Transmittance	91.0	%	ASTM D1003
Haze	2.00	%	ASTM D1003

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Optix® CP-1000I

Plaskolite, Inc. - Polymethyl Methacrylate Acrylic

Additional Information

Thermal Index, UL-746 ABC: 90°C

Burn Rate, ASTM D635: 1.7 in/min

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	150 to 165	°F
Rear Temperature	400 to 480	°F
Middle Temperature	410 to 490	°F
Front Temperature	420 to 500	°F
Nozzle Temperature	410 to 500	°F
Processing (Melt) Temp	410 to 480	°F
Mold Temperature	120 to 175	°F

Injection Notes

Heated Manifold: 410-480°F

Heated Drop (Sprue): 410-480°F

Notes

¹ Typical properties: these are not to be construed as specifications.