



POLYREX® PG-22

CHI MEI CORPORATION - General Purpose Polystyrene

Tuesday, November 5, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
RoHS Compliance	• RoHS Compliant		
Resin ID (ISO 1043)	• >PS<		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity ²	1.05		ASTM D792
Density (73°F)	1.04	g/cm ³	ISO 1183
Melt Mass-Flow Rate (200°C/5.0 kg)	18	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (200°C/5.0 kg)	19	cm ³ /10min	ISO 1133
Molding Shrinkage	0.40 to 0.70	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ³ (Break)	6030	psi	ASTM D638
Tensile Stress (Break)	5800	psi	ISO 527-2/50
Tensile Elongation ³ (Break)	2.0	%	ASTM D638
Tensile Strain (Break)	3.0	%	ISO 527-2/50
Flexural Modulus ⁴	440000	psi	ASTM D790
Flexural Modulus ⁵	348000	psi	ISO 178
Flexural Strength ⁴	7670	psi	ASTM D790
Flexural Stress ⁵	7830	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-22°F	0.86	ft·lb/in ²	
73°F	0.95	ft·lb/in ²	
Notched Izod Impact			ASTM D256
73°F, 0.126 in	0.28	ft·lb/in	
73°F, 0.252 in	0.26	ft·lb/in	
Notched Izod Impact Strength			ISO 180/1A
-22°F	0.86	ft·lb/in ²	
73°F	0.95	ft·lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	74		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed	167	°F	
Heat Deflection Temperature (264 psi, Unannealed)	163	°F	ISO 75-2/A
Deflection Temperature Under Load (264 psi, Annealed)	174	°F	ASTM D648
Vicat Softening Temperature	189	°F	ASTM D1525 ⁶

POLYREX® PG-22

CHI MEI CORPORATION - General Purpose Polystyrene

Thermal	Nominal Value	Unit	Test Method
Vicat Softening Temperature			
--	189	°F	ISO 306/A50
--	180	°F	ISO 306/B50
CLTE - Flow	2.8E-5 to 4.4E-5	in/in/°F	ISO 11359-2
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Processing Information			
Injection	Nominal Value	Unit	
Drying Temperature	176	°F	
Drying Time	2.0 to 3.0	hr	
Rear Temperature	302 to 338	°F	
Middle Temperature	338 to 374	°F	
Front Temperature	347 to 383	°F	
Mold Temperature	104 to 158	°F	

Notes

¹ Typical properties: these are not to be construed as specifications.
² 23°C
³ 0.24 in/min
⁴ 0.11 in/min
⁵ 0.079 in/min
⁶ Rate A (50°C/h), Loading 1 (10 N)