



Pinnacle PP 5110H

Pinnacle Polymers - Polypropylene Random Copolymer

Tuesday, November 5, 2019

General Information

Product Description

10 MELT FLOW RANDOM COPOLYMER FOR INJECTION MOLDING

Pinnacle Polymers Polypropylene 5110H is made via UNIPOL™ PP technology, which utilizes gas- phase fluidized bed reactors with a high activity catalyst system to ensure uniform physical properties and lot-to-lot consistency.

This product is intended for general purpose injection molding applications. This product contains a nucleation and antistatic additive package.

The 5110H product provides:

- Improved FDA food contact status
- Superior color and processing stability
- Low odor
- Good flow and set-up behavior
- Antistatic properties
- Excellent lot-to-lot consistency

Pinnacle 5110H as marketed by Pinnacle Polymers Company, in natural, uncolored pellet form is cleared by way of FCN 1538 for use in single- and repeated-use articles intended to contact all types of food under the Food and Drug Administration's (FDA) Conditions of Use A through H. FDA has not evaluated the use of this product in contact with infant formula or breast milk.

General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Additive	• Antistatic	• Nucleating Agent	
Features	• Antistatic • Food Contact Acceptable • Good Color Stability	• Good Flow • Good Processing Stability • Low Odor	• Nucleated • Random Copolymer
Uses	• General Purpose		
Agency Ratings	• FDA Food Contact, Unspecified Rating		
Forms	• Pellets		
Processing Method	• Injection Molding		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ASTM D1505
Melt Mass-Flow Rate (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield, 0.126 in, Injection Molded)	4100	psi	ASTM D638
Tensile Elongation ² (Yield, 0.126 in, Injection Molded)	12	%	ASTM D638
Flexural Modulus - 1% Secant ³ (0.126 in, Injection Molded)	137000	psi	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ⁴ (73°F, 0.126 in, Injection Molded)	1.1	ft·lb/in	ASTM D256
Notched Izod Impact (Area) ⁴			ASTM D256
73°F, 0.126 in, Injection Molded	2.47	ft·lb/in ²	

UL and the UL logo are trademarks of UL LLC © 2019. All Rights Reserved.

The information presented here was acquired by UL from the producer of the product or material or original information provider. However, UL assumes no responsibility or liability for the accuracy of the information contained on this website and strongly encourages that upon final product or material selection information is validated with the manufacturer. This website provides links to other websites owned by third parties. The content of such third party sites is not within our control, and we cannot and will not take responsibility for the information or content.

Pinnacle PP 5110H

Pinnacle Polymers - Polypropylene Random Copolymer

Notes

¹ Typical properties: these are not to be construed as specifications.

² Type I, 2.0 in/min

³ Type I, 0.050 in/min

⁴ Type I