



Thermylene® P4-30FG-0522

Asahi Kasei Plastics North America Inc. - Polypropylene

Tuesday, November 5, 2019

General Information

Product Description

PP-GF30FR

30% Glass Fiber Fiber Reinforcement with Flame Retardant (FR)

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
Filler / Reinforcement	• Asia Pacific • Glass Fiber, 30% Filler by Weight		
Additive	• Flame Retardant		
Features	• Flame Retardant		

ASTM & ISO Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density	1.45	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Mechanical			
Tensile Stress	10200	psi	ISO 527-2
Flexural Modulus	972000	psi	ISO 178
Flexural Stress	16000	psi	ISO 178
Impact			
Charpy Notched Impact Strength	5.2	ft-lb/in ²	ISO 179
Thermal			
Heat Deflection Temperature (264 psi, Unannealed)	279	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.