



Thermylene® P8-32FG-2610

Asahi Kasei Plastics North America Inc. - Polypropylene

Tuesday, November 5, 2019

General Information

Product Description

PP-GF32

32% Glass Fiber Reinforcement

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
Filler / Reinforcement	• Asia Pacific • Latin America		
Automotive Specifications	• Glass Fiber, 32% Filler by Weight	• CHRYSLER MS-DB-500 CPN 4825	• GM GMW15702-150049

ASTM & ISO Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	12800	psi	ISO 527-2
Flexural Modulus	885000	psi	ISO 178
Flexural Stress	19300	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	4.7	ft-lb/in ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	293	°F	ISO 75-2/A

Notes

¹ Typical properties: these are not to be construed as specifications.