



# Ultrason® S 2010 G4

## BASF Corporation - Polysulfone

Tuesday, November 5, 2019

### General Information

#### Product Description

Ultrason S 2010 G4 is a 20% glass reinforced, medium viscosity injection molding PSU grade with high rigidity and strength.

#### Applications

Typical applications include circuit breaker parts, lamp holders, heat shields, impellers, and printer cartridges.

#### General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Features	• High Rigidity	• High Strength	• Medium Viscosity
Uses	• Printer Parts		
Agency Ratings	• EC 1907/2006 (REACH)		
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		
Processing Method	• Injection Molding		

### ASTM & ISO Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.38	g/cm <sup>3</sup>	ISO 1183
Melt Volume-Flow Rate (MVR) (360°C/10.0 kg)	40	cm <sup>3</sup> /10min	ISO 1133
Molding Shrinkage			ISO 294-4
Across Flow	0.52	%	
Flow	0.31	%	
Water Absorption (Saturation, 73°F)	0.70	%	ISO 62
Water Absorption (Equilibrium, 73°F, 50% RH)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	957000	psi	ISO 527-2
Tensile Stress (Break, 73°F)	16700	psi	ISO 527-2
Tensile Strain (Break, 73°F)	2.9	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-22°F	3.8	ft·lb/in <sup>2</sup>	
73°F	3.8	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179
-22°F	26	ft·lb/in <sup>2</sup>	
73°F	24	ft·lb/in <sup>2</sup>	
Notched Izod Impact Strength			ISO 180
-22°F	3.8	ft·lb/in <sup>2</sup>	
73°F	3.8	ft·lb/in <sup>2</sup>	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness	24700	psi	ISO 2039-1

# Ultrason® S 2010 G4

## BASF Corporation - Polysulfone

Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (264 psi, Unannealed)	363	°F	ISO 75-2/A
CLTE - Flow	1.4E-5	in/in/°F	
RTI Elec			UL 746
0.06 in	320	°F	
0.12 in	320	°F	
RTI Imp			UL 746
0.06 in	284	°F	
0.12 in	284	°F	
RTI Str			UL 746
0.06 in	320	°F	
0.12 in	320	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+15	ohms·cm	IEC 60093
Electric Strength	1200	V/mil	IEC 60243-1
Dielectric Constant			IEC 60250
100 Hz	3.50		
1 MHz	3.50		
Dissipation Factor			IEC 60250
100 Hz	1.0E-3		
1 MHz	6.0E-3		
Comparative Tracking Index	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in	V-1		
0.12 in	V-0		

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.