

Amilan™ CM1001G-20 Nylon 6

TECHNICAL DATA

Product Description

High flow, GF20%

Uses

- Appliance Components
- Construction Applications
- Electrical/Electronic Applications
- Office Automation Equipment
- Sporting Goods
- White Goods & Small Appliances

Processing Method

- Injection Molding

ISO Designation

- >PA6-GF20<

Type

- Nylon6/Reinforced

ASTM & ISO Properties

Physical	Dry	Water Absorption	Unit	Test Method
Density (23°C)	1.29	--	g/cm³	ISO 1183
Molding Shrinkage ¹				Internal Method
Across Flow : 3.00 mm	0.60 to 0.90	--	%	
Flow : 3.00 mm	0.30 to 0.50	--	%	
Water Absorption ²				ISO 62
24 hr, 23°C	1.3	--	%	
Saturation, 23°C	7.8	--	%	
Mechanical	Dry	Water Absorption	Unit	Test Method
Tensile Strength (23°C)	120	--	MPa	ISO 527-2
Tensile Strain				ISO 527-2
Break, -40°C	2.5	3.0	%	
Break, 23°C	3.0	4.5	%	
Break, 80°C	5.0	5.5	%	
Flexural Modulus				ISO 178
-40°C	8700	7300	MPa	
23°C	6800	3500	MPa	
80°C	3200	2600	MPa	
Flexural Stress				ISO 178
-40°C	275	--	MPa	
23°C	205	--	MPa	
80°C	115	--	MPa	
Compressive Stress				ISO 604
-40°C	240	--	MPa	
23°C	155	80	MPa	
80°C	90	--	MPa	
Shear Strength (23°C)	115	65	MPa	ASTM D732
Taber Abrasion Resistance				ISO 9352
1000 Cycles	12	--	mg	
Coefficient of Friction - vs. Metal ³	0.30	--		Suzuki Method

Toray Industries, Inc.



Impact	Dry	Water Absorption	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-40°C	6.0	7.0	kJ/m ²	
23°C	7.0	8.5	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179
-40°C	25.0	30.0	kJ/m ²	
23°C	55.0	70.0	kJ/m ²	
Hardness	Dry	Water Absorption	Unit	Test Method
Rockwell Hardness				ISO 2039-2
M-Scale, 23°C	92	--		
R-Scale, 23°C	120	--		
Thermal	Dry	Water Absorption	Unit	Test Method
Deflection Temperature Under Load				
0.45 MPa, Unannealed	215	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	185	--	°C	ISO 75-2/A
Melting Temperature	225	--	°C	DSC
Specific Heat	1600	--	J/kg/°C	
Thermal Conductivity	0.33	--	W/m/K	
Coefficient of Linear Thermal Expansion	3	--	cm ³ /cm/°C	ISO 11359-2
Electrical	Dry	Water Absorption	Unit	Test Method
Volume Resistivity	1.0E+13	1.0E+10	ohms·m	IEC 60093
Electric Strength	20	--	kV/mm	IEC 60243-1
Dielectric Constant				IEC 60250
23°C, 50 Hz	4.6	--		
23°C, 1 kHz	4.4	--		
23°C, 1 MHz	3.8	--		
Dissipation Factor				IEC 60250
23°C, 50 Hz	0.040	--		
23°C, 1 kHz	0.040	--		
23°C, 1 MHz	0.030	--		
Arc Resistance	120	--	sec	UL 746
Flammability	Dry	Water Absorption	Unit	Test Method
Flame Rating (1.5 mm)	HB	HB		UL 94

Additional Information

Dry Water Absorption Moisture Content 3.0%

Notes

¹ 80x80x3mm

² in water

³ Without Lubrication

Toray Industries, Inc.

