



Nylon Resin
Amilan™

MENU

- ▶ Introduction
- ▶ List of Grade
- ▶ Technical data(Grade)
- ▶ Technical data(Porperty)
- ▶ Topics

CONTENTS

- ▶ Catalogue download
- ▶ Press release
- ▶ Overseas branch
- ▶ Related links
- ▶ Contact
- ▶ Inquiry

Basic physical properties

CM1061

Extrusion and blow molding / For blow molding / Unreinforced Nylon6 / (high viscosity blow molding)

Property				Test Method ISO	Units	CM1061	
						Dry	3.5%water
Physical property	Reinforcing Material Content			-	wt%	-	
	Specific Gravity			1138	kg/m ³	1130	-
	Water Absorption	24hrs, in 23 °C water		62	%	1.8	-
		23 °C in water				10.5	-
Mechanical property	Tensile Yield Strength		-40 °C	527-1,-2	MPa	110	100
			23 °C			80	35
			80 °C			30	20
	Elongation at Break		-40 °C	527-1,-2	%	3.0	3.0
			23 °C			40<	50<
			80 °C			50<	50<
	Flexural Strength		-40 °C	178	MPa	-	-
			23 °C			100	40
			80 °C			-	-
	Flexural Modulus		-40 °C	178	GPa	-	-
			23 °C			2.6	0.8
			80 °C			-	-
	Sharpy Impact	v-notched	-40 °C	179	kJ/m ²	-	-
		v-notched	23 °C			6.0	42.0
			unnotched	23 °C	179	kJ/m ²	-
	Rockwell Hardness		23 °C	2039-2	R-scale	119	-
	Taber Abrasion				mg/1000 cycles	3~4	-
Heat property	Melting Point			DSC Method	°C	225	-
	Coef. of Linear Thermal Expansion			11359	×10 ⁻⁵ / °C	8	-
	Heat Deflection Temp	0.46MPa		75-2	°C	182	-
		1.86MPa				65	-
	UL-94 Flame Class			UL-94	-	-	-
Electrical property	Volume Resistivity			IEC 93	Ω•m	10 ^{12~13}	10 ^{9~10}
	Dielectric Strength(3mmt)			IEC 243-1	MV/m	20	-
	Dielectric Constant 23 °C, 60%RH		1MHz	IEC 250	-	3.4	4.5
	Dissipation Factor 23 °C, 60%RH		1MHz	IEC 250	-	0.03	0.13
	Arc Resistance Tungsten			UL746A	sec.	-	-

ABS Resin
TOYOLAC
Nylon Resin
Amilan™
PBT Resin
TORAYCON
PPS Resin
TORELINA
LCP Resin
SIVERAS
Super EP
TI Polymer
Polyolefin Foam
TORAYPEF



	Electrode				
	IEC tracking Index(CTI)	UL746B		-	-

Notes:These values are typical data for this product under specific test conditions and notintended for use as limiting specifications.

[Plastics Top](#)

Copyright 2006 Toray Industries, Inc.All rights reserved.

[> Terms and Conditions](#) [> Privacy Policy](#) [> Site map](#) [↑](#)

