

Property	Test Condition	Test Method ISO	Units	Nylon66/Reinforced
				Heat stability, GF33%
				CM3006G33
				>PA66-GF33<
Physical property				
Density	23℃	ISO1183	kg/m ³	1410
Mechanical property				
Tensile strength	23℃	ISO527-1,2	MPa	198
Elongation at Break	23℃	ISO527-1,2	%	3
Flexural Strength	23℃	ISO178	MPa	290
Flexural Modulus	23℃	ISO178	GPa	9.7
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	12.8

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

