

Amilan™ U625 X21

Nylon 66

TECHNICAL DATA

Product Description

Super high impact, Soft

Uses

- Appliance Components
- Construction Applications
- Electrical/Electronic Applications
- Office Automation Equipment
- Rubber Replacement
- Sporting Goods
- White Goods & Small Appliances

Processing Method

- Injection Molding

ISO Designation

- >PA66-I<

Type

- Nylon66/High impact

ASTM & ISO Properties

Physical	Dry	Water Absorption	Unit	Test Method
Density (23°C)	1.08	--	g/cm ³	ISO 1183
Molding Shrinkage ¹ (3.00 mm)	2.00 to 2.10	--	%	Internal Method
Water Absorption ²				ISO 62
24 hr, 23°C	1.3	--	%	
Saturation, 23°C	7.0	--	%	
Mechanical	Dry	Water Absorption	Unit	Test Method
Tensile Strength				ISO 527-2
-40°C	80	--	MPa	
23°C	55	40	MPa	
Tensile Strain				ISO 527-2
Break, -40°C	20	--	%	
Break, 23°C	40	> 50	%	
Flexural Modulus				ISO 178
-40°C	2400	--	MPa	
23°C	1900	700	MPa	
Flexural Stress				ISO 178
-40°C	105	--	MPa	
23°C	70	35	MPa	
Taber Abrasion Resistance				ISO 9352
1000 Cycles	7 to 8	--	mg	
Impact	Dry	Water Absorption	Unit	Test Method
Charpy Notched Impact Strength				ISO 179
-40°C	14.0	--	kJ/m ²	
23°C	89.0	100.0	kJ/m ²	
Hardness	Dry	Water Absorption	Unit	Test Method
Rockwell Hardness				ISO 2039-2
R-Scale, 23°C	114	--		

Toray Industries, Inc.



Thermal	Dry	Water Absorption	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/A
1.8 MPa, Unannealed	63	--	°C	
Melting Temperature	265	--	°C	DSC
Coefficient of Linear Thermal Expansion	10 to 11	--	cm ³ -5/cm/°C	ISO 11359-2

Additional Information

Dry Water absorption Moisture Content 2.0%

Notes

¹ 80x80x3mm

² in water

Toray Industries, Inc.

