

Property	Test Condition	Test Method ISO	Units	High Impact/Nylon66	
				Super high impact, Soft	
				U625X21	
				>PA66-I<	
				Dry	2.0%water
Physical property					
Water Absorption	24hrs. in 23℃ water	ISO62	%	1.3	-
Water Absorption	23℃ in water	ISO62	%	7	-
Density	23℃	ISO1183	kg/m ³	1080	-
Mechanical property					
Tensile strength	-40℃	ISO527-1,2	MPa	80	-
Tensile strength	23℃	ISO527-1,2	MPa	55	40
Elongation at Break	-40℃	ISO527-1,2	%	20	-
Elongation at Break	23℃	ISO527-1,2	%	40	50
Flexural Strength	-40℃	ISO178	MPa	105	-
Flexural Strength	23℃	ISO178	MPa	70	35
Flexural Modulus	-40℃	ISO178	GPa	2.4	-
Flexural Modulus	23℃	ISO178	GPa	1.9	0.7
Coefficient of friction (Without lubrication)	Vs metal	Suzuki Method	-	-	-
Rockwell Hardness	80℃	ISO2039-2	R Scale	114	-
Taper Abrasion		ISO9352	mg/1000times	7~8	-
Charpy Impact Strength (V-notched)	-40℃	ISO179	kJ/m ²	14	-
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	89	100
Charpy Impact Strength (Unnotched)	23℃	ISO179	kJ/m ²	-	-
Heat property					
Melting Point		DSC Method	℃	265	-
Coef of Linear Thermal Expansion		ISO11359-2	×10 ⁻⁵ /℃	10~11	-
Heat Deflection Temp Low Load	0.45MPa	ISO75-1,2	℃	-	-
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	℃	63	-
Molding property					
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	-	-
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	2.0~2.1	-

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

