

Property	Test Condition	Test Method ISO	Units	High Impact/Nylon66
				High Impact
				UTN310
				>PA66-I<
Physical property				
Density	23℃	ISO1183	kg/m ³	1120
Mechanical property				
Tensile strength	23℃	ISO527-1,2	MPa	70
Elongation at Break	23℃	ISO527-1,2	%	25
Flexural Strength	23℃	ISO178	MPa	95
Flexural Modulus	23℃	ISO178	GPa	2.4
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	12

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

