

GLAMIDE™ T-663G50

TOYOBO MC Corporation - Polyamide 66

General Information

Product Description

GF Reinforced

General

Material Status	• Commercial: Active
Filler / Reinforcement	• Glass Fiber, 50% Filler by Weight
Uses	• Automotive Applications • Automotive Exterior Parts • General Purpose • Industrial Applications
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PA66-GF50<
Revision Date	• 9/4/2025

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density	1.57	g/cm ³	ISO 1183
Molding Shrinkage ¹			Internal Method
Flow : 2.00 mm	0.20	%	
Across Flow : 2.00 mm	0.60	%	
Water Absorption (24 hr, 23°C)	0.80	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	210	MPa	ISO 527
Tensile Elongation (Break)	2.0	%	ISO 527
Flexural Modulus	15300	MPa	ISO 178
Flexural Strength	340	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-40°C	11	kJ/m ²	
23°C	15	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	260	°C	ISO 75-2/B
1.8 MPa, Unannealed	255	°C	ISO 75-2/A
CLTE - Flow	1.9E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	IEC 60250



GLAMIDE™ T-663G50
TOYOBO MC Corporation - Polyamide 66

Processing Information		
Injection		Unit
Drying Temperature	100 to 120	°C
Drying Time	3.0 to 5.0	hr
Middle Temperature	270 to 300	°C
Front Temperature	270 to 300	°C
Nozzle Temperature	270 to 300	°C
Mold Temperature	80 to 100	°C

Notes

¹ 100×100×2mmt, film gate

