

GLAMIDE™ TY-155TNH

TOYOBO MC Corporation - Polyamide 6

General Information

Product Description

GF Reinforced

General

Material Status	• Commercial: Active
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Pleasing Surface Appearance
Uses	• Automotive Applications • General Purpose • Automotive Exterior Parts • Industrial Applications
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PA6-GF30<
Revision Date	• 9/5/2025

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density	1.36	g/cm ³	ISO 1183
Molding Shrinkage ¹			Internal Method
Flow : 2.00 mm	0.30	%	
Across Flow : 2.00 mm	0.60	%	
Water Absorption (24 hr, 23°C)	1.5	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	165	MPa	ISO 527-2
Tensile Strain (Break)	2.7	%	ISO 527-2
Flexural Modulus	7600	MPa	ISO 178
Flexural Stress	220	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-40°C	8.0	kJ/m ²	
23°C	9.5	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	215	°C	ISO 75-2/B
1.8 MPa, Unannealed	200	°C	ISO 75-2/A
CLTE - Flow	2.5E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	IEC 60250
Additional Information			
65% equilibrium relative humidity			



GLAMIDE™ TY-155TNH
TOYOBO MC Corporation - Polyamide 6

Processing Information		
Injection		Unit
Drying Temperature	100 to 120	°C
Drying Time	3.0 to 5.0	hr
Hopper Temperature	230 to 240	°C
Middle Temperature	240 to 270	°C
Front Temperature	240 to 270	°C
Nozzle Temperature	240 to 270	°C
Mold Temperature	80 to 100	°C

Notes

¹ 100×100×2mmt, film gate

