

GLAMIDE™ TY-262LS

TOYOBO MC Corporation - Polyamide 66

General Information

Product Description

GF Reinforced

General

Material Status	• Commercial: Active
Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Features	• Wear Resistant
Uses	• Automotive Applications • Automotive Exterior Parts • General Purpose • Industrial Applications
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PA66-GF35<
Revision Date	• 9/10/2025

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ISO 1183
Molding Shrinkage ¹			Internal Method
Flow : 2.00 mm	0.30	%	
Across Flow : 2.00 mm	0.80	%	
Water Absorption (24 hr, 23°C)	1.1	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	195	MPa	ISO 527
Tensile Elongation (Break)	3.2	%	ISO 527
Flexural Modulus	10400	MPa	ISO 178
Flexural Strength	270	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-40°C	9.0	kJ/m ²	
23°C	11	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	260	°C	ISO 75-2/B
1.8 MPa, Unannealed	250	°C	ISO 75-2/A
CLTE - Flow	2.3E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	IEC 60250



GLAMIDE™ TY-262LS
TOYOBO MC Corporation - Polyamide 66

Processing Information		
Injection		Unit
Drying Temperature	100 to 120	°C
Drying Time	3.0 to 5.0	hr
Middle Temperature	270 to 290	°C
Front Temperature	270 to 290	°C
Nozzle Temperature	270 to 290	°C
Mold Temperature	80 to 100	°C

Notes

¹ 100×100×2mmt, film gate

