

GLAMIDE™ TY-752GDQ

TOYOBO MC Corporation - Polyamide 6I

General Information

Product Description

GF Reinforced

General

Material Status	• Commercial: Active
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Low Temperature Impact Resistance • Pleasing Surface Appearance
Uses	• Automotive Applications • General Purpose • Electrical/Electronic Applications • Industrial Applications
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PA6-I-GF30<
Revision Date	• 9/10/2025

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.30	g/cm ³	ISO 1183
Molding Shrinkage ¹			Internal Method
Flow : 2.00 mm	0.20	%	
Across Flow : 2.00 mm	0.60	%	
Water Absorption (24 hr, 23°C)	1.0	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	115	MPa	ISO 527
Tensile Elongation (Break)	4.0	%	ISO 527
Flexural Modulus	6600	MPa	ISO 178
Flexural Strength	180	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	27	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2
0.45 MPa, Unannealed	215	°C	
1.8 MPa, Unannealed	190	°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms-cm	IEC 60250



GLAMIDE™ TY-752GDQ
TOYOBO MC Corporation - Polyamide 6I

Processing Information		
Injection		Unit
Drying Temperature	100 to 120	°C
Drying Time	3.0 to 5.0	hr
Hopper Temperature	230 to 250	°C
Middle Temperature	250 to 270	°C
Front Temperature	250 to 270	°C
Nozzle Temperature	250 to 270	°C
Mold Temperature	80 to 100	°C

Notes

¹ 100×100×2mmt, film gate

