

PRODUCT CODE	HYPERPOL AP 10D03 R01
PRODUCT DESCRIPTION	PPA, 10% GLASS FIBER REINFORCED, NATURAL

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm ³	1.26-1.28
	MOLDING SHRINKAGE	PARALLEL/NORMAL	ISO 294-4	%	0.4-0.6
	MOISTURE CONTENT	-	ISO 15512	%	<0.1

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	100-110
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	-
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	-
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	5500-6500
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	kJ/m ²	-
	IZOD IMPACT STRENGTH, NOTCHED	-30°C	ISO 180/A	kJ/m ²	-
	IZOD IMPACT STRENGTH, UNNOTCHED	+23°C	ISO 180/U	kJ/m ²	22-26
	IZOD IMPACT STRENGTH, UNNOTCHED	-30°C	ISO 180/U	kJ/m ²	-

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	-
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	-
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	-
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	320-325

PRODUCT CODE	HYPERPOL AP 10D03 R01
PRODUCT DESCRIPTION	PPA, 10% GLASS FIBER REINFORCED, NATURAL

ELECTRICAL&FLAMMABILITY	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	HB
	FLAME RATING	1,6 mm	UL 94	-	HB
	GLOW WIRE FLAMMABILITY INDEX	2 mm	IEC 60695	°C	-
	GLOW WIRE IGNITABILITY TEMPERATURE	2 mm	IEC 60695	°C	-
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	-
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	1E+15
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	1E+15

INJECTION PROCESS	PROPERTIES	UNITS	VALUE
	PREDRYING TEMPERATURE	°C	120
	PREDRYING TIME	hours	2-4
	MELTING TEMPERATURE	°C	330-350
	NOZZLE TEMPERATURE	°C	330
	PRE-3 REGION TEMPERATURE	°C	330-340
	MID-2 REGION TEMPERATURE	°C	330-340
	AFT-1 REGION TEMPERATURE	°C	330-340
	MOLD TEMPERATURE	°C	120-160
	HOLD PRESSURE	MPa	-