

PRODUCT CODE	HYPERPOL SP 10D03 R01
PRODUCT DESCRIPTION	PPS %10 GLASS FIBER REINFORCED

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm ³	1.41-1.44
	MOLDING SHRINKAGE	PARALLEL/ NORMAL	ISO 294-4	%	0.3-0.5
	MOISTURE CONTENT	-	ISO 15512	%	0.02-0.04

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	110-120
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	-
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	1.5-2
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	5500-6500
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	kJ/m ²	7-10
	IZOD IMPACT STRENGTH, NOTCHED	-30°C	ISO 180/A	kJ/m ²	-
	IZOD IMPACT STRENGTH, UNNOTCHED	+23°C	ISO 180/U	kJ/m ²	-
	IZOD IMPACT STRENGTH, UNNOTCHED	-30°C	ISO 180/U	kJ/m ²	-

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	-
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	260-285
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	235-260
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	310-330
	BALL PRESSURE TEST	120 °C	ISO 60695-10-2	-	-

PRODUCT CODE	HYPERPOL SP 10D03 R01
PRODUCT DESCRIPTION	PPS %10 GLASS FIBER REINFORCED

ELECTRICAL&FLAMMABILITY	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	V0
	FLAME RATING	1,6 mm	UL 94	-	V0
	GLOW WIRE FLAMMABILITY INDEX	2 mm	IEC 60695	°C	960
	GLOW WIRE IGNITABILITY TEMPERATURE	2 mm	IEC 60695	°C	-
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	-
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	1E+16
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	-

INJECTION PROCESS	PROPERTIES	CONDITION	VALUE
	PREDRYING TEMPERATURE	°C	140-150
	PREDRYING TIME	hours	5-6
	MELTING TEMPERATURE	°C	320-340
	NOZZLE TEMPERATURE	°C	330-340
	PRE- 3 REGION TEMPERATURE	°C	310-320
	MID-2 REGION TEMPERATURE	°C	320-330
	AFT-1 REGION TEMPERATURE	°C	330-345
	MOLD TEMPERATURE	°C	140-170
	HOLD PRESSURE	MPa	-