

Torayca™ 3101T-10V

Nylon 66

TECHNICAL DATA

Product Description

CF10%

Uses

- Automotive Applications
- Gears
- Printer

Processing Method

- Injection Molding

ISO Designation

- >PA66-CF10<

Type

- Short carbon fiber reinforced PA66

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.18	g/cm ³	ISO 1183
Molding Shrinkage ¹			Internal Method
Across Flow : 3.00 mm	1.00	%	
Flow : 3.00 mm	0.40	%	
Water Absorption ² (Saturation, 23°C)	2.3	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	175	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.8	%	ISO 527-2
Flexural Modulus (23°C)	8200	MPa	ISO 178
Flexural Stress (23°C)	235	MPa	ISO 178
Amount of Wear - vs. S45C ³	1.0	mg/hr	Suzuki Method
Coefficient of Friction - vs. S45C ³	0.33		Suzuki Method
Limiting Pressure Velocity - vs. S45C	2.3	MPa·m/s	Suzuki Method
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	5.1	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
1.8 MPa, Unannealed	245	°C	
Melting Temperature	265	°C	DSC
CLTE			ISO 11359-2
Flow	4.1	cm ³ /cm/°C	
Transverse	3.7	cm ³ /cm/°C	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.79 mm)	HB		UL 94

Notes

¹ 80x80x3mm

² 50% RH

³ 1MPa, 0.33 m/s

