

Grilon TSGK-30 X

PA666-(GF+GB)30

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

Product designation according to ISO 1874:

PA66+PA6, MHR, 14-080N, (GF+GB)30X

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	8500 / 5700	MPa	ISO 527-1/-2
Stress at break	155 / 85	MPa	ISO 527-1/-2
Strain at break	3 / 10	%	ISO 527-1/-2
Charpy impact strength (+23°C)	50 / 75	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	45 / 45	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	8 / 13	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	7 / 7	kJ/m ²	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	200 / 100	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	260 / -	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	215 / -	°C	ISO 75-1/-2
Temp. of deflection under load (8.00 MPa)	80 / -	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	60 / -	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	80 / -	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	HB / -	class	IEC 60695-11-10
Thickness tested	0.8 / -	mm	IEC 60695-11-10
Max. usage temperature (long term)	90 - 120	°C	ISO 2578
Max. usage temperature (short term)	220	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	1E12 / 1E10	Ohm*m	IEC 60093
Surface resistivity	- / 1E11	Ohm	IEC 60093
Electric strength	24 / 23	kV/mm	IEC 60243-1
Comparative tracking index	- / 425	-	IEC 60112


Other properties	dry / cond	Unit	Test Standard
Water absorption	7 / -	%	Sim. to ISO 62
Humidity absorption	2.5 / -	%	Sim. to ISO 62
Density	1340 / -	kg/m ³	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	0.1 / -	%	ISO 294-4, 2577
Molding shrinkage (normal)	0.7 / -	%	ISO 294-4, 2577

Diagrams




Viscosity-shear rate




Shearstress-shear rate




Stress-strain




Stress-strain




Secant modulus-strain




Secant modulus-strain



Specific volume-temperature (pvT)



Tensile modulus-temperature



Characteristics

Processing

Injection Molding

Delivery form

Granules

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa

Chemical Media Resistance

Automotive

Interior

Electricals & Electronics

Electrical appliances

Industry & Consumer goods

Housewares, Mechanical Engineering, Sports & Leisure, Tools & Accessories



Acids

- ☺ Acetic Acid (5% by mass) (23°C)
- ☺ Citric Acid solution (10% by mass) (23°C)
- ☺ Lactic Acid (10% by mass) (23°C)
- ☹ Hydrochloric Acid (36% by mass) (23°C)
- ☹ Nitric Acid (40% by mass) (23°C)
- ☹ Sulfuric Acid (38% by mass) (23°C)
- ☹ Sulfuric Acid (5% by mass) (23°C)
- ☹ Chromic Acid solution (40% by mass) (23°C)

Bases

- ☺ Sodium Hydroxide solution (35% by mass) (23°C)
- ☺ Sodium Hydroxide solution (1% by mass) (23°C)
- ☺ Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

- ☺ Isopropyl alcohol (23°C)
- ☺ Methanol (23°C)
- ☺ Ethanol (23°C)

Hydrocarbons

- ☺ n-Hexane (23°C)
- ☺ Toluene (23°C)
- ☺ iso-Octane (23°C)

Ketones

- ☺ Acetone (23°C)

Ethers

- ☺ Diethyl ether (23°C)

Mineral oils

- ☺ SAE 10W40 multigrade motor oil (23°C)
- ☺ SAE 10W40 multigrade motor oil (130°C)
- ☺ SAE 80/90 hypoid-gear oil (130°C)
- ☺ Insulating Oil (23°C)

Standard Fuels

- ☺ ISO 1817 Liquid 1 (60°C)
- ☺ ISO 1817 Liquid 2 (60°C)
- ☺ ISO 1817 Liquid 3 (60°C)
- ☺ ISO 1817 Liquid 4 (60°C)
- ☺ Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
- ☺ Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)
- ☺ Diesel fuel (pref. ISO 1817 Liquid F) (23°C)
- ☺ Diesel fuel (pref. ISO 1817 Liquid F) (90°C)
- ☺ Diesel fuel (pref. ISO 1817 Liquid F) (>90°C)

Salt solutions



- ☹ Sodium Chloride solution (10% by mass) (23°C)
- 🚫 Sodium Hypochlorite solution (10% by mass) (23°C)
- ☹ Sodium Carbonate solution (20% by mass) (23°C)
- ☹ Sodium Carbonate solution (2% by mass) (23°C)
- ☹ Zinc Chloride solution (50% by mass) (23°C)

Other

- ☹ Ethyl Acetate (23°C)
- 🚫 Hydrogen peroxide (23°C)
- ☹ DOT No. 4 Brake fluid (130°C)
- ☹ Ethylene Glycol (50% by mass) in water (108°C)
- ☹ 1% nonylphenoxy-polyethyleneoxy ethanol in water (23°C)
- ☹ 50% Oleic acid + 50% Olive Oil (23°C)
- ☹ Water (23°C)
- ☹ Deionized water (90°C)
- 🚫 Phenol solution (5% by mass) (23°C)

