

PELPRENE™ C-1203
TOYOBO MC Corporation - Thermoplastic Copolyester Elastomer

General Information		
Product Description		
Special Grade		
General		
Material Status	• Commercial: Active	
Features	• Heat Aging Resistant	
Uses	• Automotive Applications • Automotive Interior Parts	• General Purpose • Industrial Applications
Appearance	• Black	• Natural Color
Forms	• Pellets	
Processing Method	• Extrusion	• Injection Molding
Part Marking Code (ISO 11469)	• >TPC-ES<	
Revision Date	• 8/27/2025	

ASTM & ISO Properties			
Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.9	g/10 min	ASTM D1238
Molding Shrinkage ¹			Internal Method
Flow : 2.00 mm	0.90	%	
Across Flow : 2.00 mm	1.0	%	
Water Absorption ² (Equilibrium, 23°C, 50% RH)	0.14	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	269	MPa	ISO 527
Tensile Strength			
Break	36.1	MPa	ISO 37
50% Strain	10.5	MPa	ISO 527
Tensile Elongation (Break)	600	%	ISO 37
Flexural Modulus	110	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	No Break		ISO 179
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 48-4
Shore A, 15 sec	96		
Shore D, 15 sec	47		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Annealed)	56.0	°C	ISO 75-2/B
Brittleness Temperature	< -65.0	°C	ISO 974
Melting Temperature	201	°C	Internal Method
CLTE			ISO 11359-2
Flow	1.4E-4	cm/cm/°C	
Transverse	1.4E-4	cm/cm/°C	



PELPRENE™ C-1203
TOYOBO MC Corporation - Thermoplastic Copolyester Elastomer

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	4.4E+16	ohms	IEC 62631-3-2
Volume Resistivity	9.9E+12	ohms·m	IEC 62631-3-1

Processing Information		
Injection	Unit	
Drying Temperature	100 to 120	°C
Drying Time	4.0	hr
Rear Temperature	200 to 230	°C
Middle Temperature	220 to 240	°C
Front Temperature	220 to 240	°C

- Notes
- ¹ 100×100×2mmt, Film gate
- ² 192hr

