

PELPRENE™ P-150B

TOYOBO MC Corporation - Thermoplastic Copolyester Elastomer

General Information

Product Description

General Grade

General

Material Status	• Commercial: Active		
Features	• High Hardness		
Uses	• Automotive Applications • Automotive Interior Parts	• General Purpose • Industrial Applications	• Sporting Goods
Forms	• Pellets		
Processing Method	• Injection Molding		
Part Marking Code (ISO 11469)	• >TPC-ET<		
Revision Date	• 4/7/2025		

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density	1.23	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	19	g/10 min	ISO 1133
Molding Shrinkage ¹			Internal Method
Flow : 2.00 mm	1.6	%	
Across Flow : 2.00 mm	1.7	%	
Water Absorption ² (Equilibrium, 23°C, 50% RH)	0.27	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	344	MPa	ISO 527
Tensile Stress			
Yield	20.7	MPa	ISO 37
50% Strain	15.9	MPa	ISO 527
Tensile Strength (Break)	43.9	MPa	ISO 37
Tensile Elongation (Break)	660	%	ISO 37
Flexural Modulus	323	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength	No Break		ISO 179
Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 48-4
Shore A, 15 sec	98		
Shore D, 15 sec	57		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2
0.45 MPa, Unannealed	90.0	°C	
Brittleness Temperature	< -65.0	°C	ISO 974
Melting Temperature	211	°C	Internal Method
CLTE			ISO 11359-2
Flow	1.3E-4	cm/cm/°C	
Transverse	1.2E-4	cm/cm/°C	



PELPRENE™ P-150B

TOYOBO MC Corporation - Thermoplastic Copolyester Elastomer

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+16	ohms	IEC 62631-3-2
Volume Resistivity	1.5E+11	ohms·m	IEC 62631-3-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.8 mm)	HB		UL 94

Processing Information

Injection		Unit
Drying Temperature	100 to 120	°C
Drying Time	> 4.0	hr
Rear Temperature	200 to 230	°C
Middle Temperature	220 to 240	°C
Front Temperature	220 to 240	°C
Mold Temperature	20 to 40	°C

Notes

¹ 100×100×2mmt, film gate

² 192hr

