

**TAITALAC 1000D**

ABS Resin

Acrylonitrile Butadiene Styrene (ABS) Resin

Characteristics	Applications
• Injection • Medium high impact • Good flow for process • Gloss	• Telephone housing / House-ware • Office Automation • Electrical appliances • Office equipment / Kitchen appliances • plating Wheel cap / radiator grille

Properties	Test	Test Condition	SI unit	
			Unit	s.p.
Rheological Properties				
Specific Gravity	ASTM D792	23°C	g/cm³	1.03
Melt Volume Rate	ASTM D1238	200°C, 5kg load	g/10min	1.8
Melt Volume Rate	ASTM D1238	220°C, 10kg load	g/10min	18
Mechanical Properties				
Izod Impact Strength	ASTMD256	23°C, 1/4" Notched	kg-cm/cm	22
Izod Impact Strength	ASTMD256	23°C, 1/8" Notched	kg-cm/cm	25
Tensile Strength at Yield	ASTMD638	23°C, 5 mm/min	kg/cm²	430
Tensile Strength at Break	ASTMD638	23°C, 5 mm/min	kg/cm²	380
Elongation at Break	ASTMD638	23°C, 5 mm/min	%	30
Flexural Yield	ASTMD790	23°C, 2.8 mm/min	kg/cm²	720
Flexural Modulus	ASTMD790	23°C, 2.8 mm/min	kg/cm²	25000
Thermal Properties				
Heat Distortion Temperature	ASTMD648	unannealing 1.8MPa	°C	86
Vicat Softening Temperature	ASTMD1525	50°C/hr , 1 kg load	°C	103
Physical Properties				
Rockwell Hardness	ASTMD785	23°C, R-scale	R-scale	110
Mold Shrinkage	ASTMD955	60×60×2mm S _{Flow}	%	≤ 0.4
Moisture Absorption Equilibrium	ASTMD570	23°C/50% RH	wt %	≤ 0.3
Flammability				
	UL-94	1/16 inch	No E50263	HB
Electrical				
Relative Temperature Index	UL-746B	0.062 inch above	°C	60
Hot Wire Ignition	UL-746A	0.062 inch above	Secs	17
High Current Arc Ignition	UL-746A	0.062 inch above	Arcs	200
Arc Tracking Rate	UL-746A	0.062 inch above	in/min	0

