



(General Purpose Polystyrene) GPPS 818

Characteristics	Applications
- Extrusion Grade - The most state of the art from US NOVA CHEMICAL - Low Residual Monomer - Good Heat Resistance - Mold Dimension Stability - Good Transparency - Easy Processing - High M.W. - High strength	OPS/PSP sheet applications.

物理性質 Physical Properties

Properties	ISO method	Test Condition	Unit	Typical Value
Specific Gravity	ISO 1183	---	---	1.04
Melt Flow Index	ISO 1133	200°C, 5kg load	g/cm ³	2
Tensile Strength at Yield	ISO 527	23°C, 50 mm/min	kg/cm ²	53
Elongation at Break	ISO 527	23°C, 50 mm/min	%	2
Izod Impact Strength	ISO 180/1A	23°C, Izod Notched	kg-cm/cm	1.9
Vicat Softening Temperature	ISO 306	120°C/hr , 1 kg load	°C	105
Heat Distortion Temperature	ISO 75A	Unanneale 1.8MPa load pressure(Edgewise)	°C	95
Flammability	UL-94	1/16" Sample	File No. E50263	94HB
Residual SM monomer	Internal	GC	ppm	< 300
Haze	---	2.8mm thick	%	0.5

