



通用聚苯乙烯(General Purpose Polystyrene) GPPS 866N / B

特性

- 射出級
- NOVA CHEMICAL 最新生產技術
- 低殘留單體量
- 耐熱性佳
- 表面尺寸安定性佳
- 優異透明度
- 良好加工性
- 電器性佳

Characteristics

- Injection Grade
- The most state of the art from US NOVA CHEMICAL
- Low Residual Monomer
- Good Heat Resistance
- Mold Dimension Stability
- Good Transparency
- Easy Processing
- Good Electrical Properties

應用

Applications

CD-Case/Slim、家電製品、家庭五金、化妝品容器等。 CD-Case/Slim, electrical appliances, house hardwares, cassette & cosmetic cases.

物理性質 Physical Properties

Properties	Test Method	Test Condition	Unit	Typical Value
比重 Specific Gravity	ASTM D792	23℃	---	1.046
	ISO 1183		g/cm ³	1.04
流動指數 Melt Flow Index	ASTM D1238	200℃, 5 kg load	g/10min	5.0
	ISO 1133		ml/10min	5.3
抗張強度 Tensile Strength at Yield	ASTM D638	23℃, 1/8" Sample	kg/cm ²	450
	ISO 527		Mpa	44
伸長率 Elongation at Break	ASTM D638	23℃, 1/8" Sample	%	2.0
	ISO 527			
Izod 耐衝擊強度 Izod Impact Strength	ASTM D256	23℃, A method, notched 1/4"×1/2"×5/2"	kg-cm/cm	1.4
	ISO 180A	23℃ Notched	KJ/m ²	1.8
Vicat 軟化溫度 Vicat Softening Temperature	ASTM D1525	1 kg load, 3 mm Thick(120℃/hr)	℃	100
	ISO 306	1 kg load, 3 mm Thick(50℃/hr)		98
燃燒性 Flammability	UL-94	1/16" Sample	File No. E50263	94HB
殘留苯乙烯單體 Residual SM monomer	---	---	ppm	200
曇度 Haze	---	2.8mm thick	%	0.4

