

<b>PRODUCT CODE</b>	<b>TISOPLÉN D 20D01 R01</b>
<b>PRODUCT DESCRIPTION</b>	<b>PPC, 20% TALC FILLED, NATURAL</b>

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm <sup>3</sup>	<b>1.04-1.08</b>
	MOLDING SHRINKAGE	PARALLEL/NORMAL	ISO 294-4	%	-
	MOISTURE CONTENT	-	ISO 15512	%	-

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	-
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	<b>20-30</b>
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	<b>&gt;15</b>
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	<b>1000-2500</b>
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	Kj/m <sup>2</sup>	<b>&gt;7</b>
	IZOD IMPACT STRENGTH, NOTCHED	-30°C	ISO 180/A	Kj/m <sup>2</sup>	-
	IZOD IMPACT STRENGTH, UNNOTCHED	+23°C	ISO 180/U	Kj/m <sup>2</sup>	<b>NB</b>
	IZOD IMPACT STRENGTH, UNNOTCHED	-30°C	ISO 180/U	Kj/m <sup>2</sup>	<b>NB</b>

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	-
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	-
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	<b>65</b>
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	<b>160-165</b>
	BALL PRESSURE TEST	120 °C	ISO 60695-10-2	-	-

<b>PRODUCT CODE</b>	<b>TISOPLLEN D 20D01 R01</b>
<b>PRODUCT DESCRIPTION</b>	<b>PPC, 20% TALC FILLED, NATURAL</b>

<b>ELECTRICAL &amp; FLAMMABILITY</b>	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	<b>HB</b>
	FLAME RATING	1,6 mm	UL 94	-	<b>HB</b>
	GLOW WIRE FLAMMABILITY INDEX	2 mm	IEC 60695	°C	-
	GLOW WIRE IGNITABILITY TEMPERATURE	2 mm	IEC 60695	°C	-
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	-
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	<b>1E+15</b>
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	<b>1E+15</b>

<b>INJECTION PROCESS</b>	PROPERTIES	CONDITION	VALUE
	PREDRYING TEMPERATURE	°C	<b>80</b>
	PREDRYING TIME	hours	<b>1-2</b>
	MELTING TEMPERATURE	°C	<b>210-230</b>
	NOZZLE TEMPERATURE	°C	<b>230</b>
	PRE- 3 REGION TEMPERATURE	°C	<b>200-240</b>
	MID-2 REGION TEMPERATURE	°C	<b>200-240</b>
	AFT-1 REGION TEMPERATURE	°C	<b>150-180</b>
	MOLD TEMPERATURE	°C	<b>40-70</b>
	HOLD PRESSURE	MPa	<b>50-100</b>

