

FEATURE 特点

APPLICATION 用途

Automotive Parts

汽车配件,一般应用

TECHNICAL DATA SHEET 技术数据表

PROPERTY 性能	TEST METHOD 测试方法	TEST CONDITION 测试条件	UNITS 单位	TOYOLAC™ 440Y X50
Physical Properties 物理性能				
Density 密度	ISO 1183	23 °C	kg/m³	1050
Melt Flow Rate 流动系数	ISO 1133	220 °C / 10 kg	g/10 min	14
Mold Shrinkage 成型收缩率	ASTM D955	23 °C / 50% RH	%	0.4 – 0.7
Glass Content 玻纤含量	–	–	–	–
Mechanical Properties 机械性能				
Charpy Impact Strength, Notched Charpy 耐冲击强度, 缺口	ISO 179/1eA	23 °C / 50% RH	kJ/m²	16
Tensile Strength 拉伸强度-降伏点	ISO 527	50 mm / min	MPa	48
Tensile Elongation at Break 拉伸伸长率-断裂点	ISO 527	50 mm / min	%	9
Tensile Modulus 拉伸模数	–	–	–	–
Flexural Strength 弯曲强度	ISO 178	2 mm / min	MPa	75
Flexural Modulus 弯曲模数	ISO 178	2 mm / min	MPa	2400
Thermal Properties 热性能				
Deflection Temperature Under Load 热变形温度	ISO 75	1.8 MPa / 120 °C/hr	°C	90
Appearance 表面				
Glossiness 光泽度	–	–	–	–
Light Transmittance 光线透光率	–	–	–	–
Haze 模糊系数	–	–	–	–
Flammability 燃烧性				
Flammability 燃烧性	Toray Method	–	–	HB equivalent

TORAY PLASTICS (MALAYSIA) SDN BERHAD 东丽塑料大马有限公司

