

General Purpose ABS TOYOLAC™ 500 322

Property 代表物性	Test Method 试验法	Test Conditions 试验条件	Unit 单位	TOYOLAC 500 322
Physical Properties 物理性能				
Density 比重	ISO 1183	23°C	kg/m³	1050
Melt Flow Rate 流动系数	ISO 1133	220°C, 10 kg	g / 10min	20
Mechanical Properties 机械性能				
Charpy Impact, Notched 缺口冲击强度	ISO 179/1eA	23°C / 50% RH	kJ/m²	14
Tensile Strength 引张强度;降伏点	ISO 527	50 mm/min	MPa	59
Tensile Elongation at Break 拉伸伸长率		50 mm/min	%	> 10
Tensile Modulus 拉伸模数		1 mm/min	MPa	3000
Flexural Strength 弯曲强度	ISO 178	2 mm/min	MPa	89
Flexural Modulus 弯曲模数				2690
Thermal Properties 热性能				
Deflection Temperature under load 热变形温度	ISO 75	1.8 Mpa / 120°C/hr	°C	85
Flammability 燃烧性				
Flammability 燃烧性	UL 94	-	-	HB

