

Property	Test Condition	Test Method ISO	Units	Short carbon fiber reinforced P A66	
				CF10%	
				3101T-10V	
				>PA66-CF10<	
Physical property					
Content of filler		-	wt%	10	
Water Absorption	23℃×50%RH in water		%	2.3	
Density	23℃	ISO1183	kg/m ³	1180	
Mechanical property					
Tensile strength	23℃	ISO527-1,2	MPa	175	
Elongation at Break	23℃	ISO527-1,2	%	2.8	
Flexural Strength	23℃	ISO178	MPa	235	
Flexural Modulus	23℃	ISO178	GPa	8.2	
Coefficient of friction	Vs S45C、1MPa、0.33m/s	Suzuki Method	-	0.33	
Coefficient of friction	Vs SUS、1MPa、0.33m/s	Suzuki Method	-	-	
Amount of wear	Vs S45C、1MPa、0.33m/s	Suzuki Method	mg/h	1	
Amount of wear	Vs SUS、1MPa、0.33m/s	Suzuki Method	mg/h	-	
Limit of PV	Vs S45C	Suzuki Method	Mpa · m/s	2.3	
Limit of PV	Vs SUS	Suzuki Method	Mpa · m/s	-	
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	5.1	
Heat property					
Melting Point		DSC Method	℃	265	
Coef of Linear Thermal Expansion		ISO11359-2	×10 ⁻⁵ /℃	3.8	
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	℃	245	
Flammability		UL94	rank/thickness m mt	HBEquivalent	
Electrical property					
Volume Resistivity		IEC60093	Ω · m	10 ⁻¹	
Molding property					
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	0.4	
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	1.1	

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

