

Property	Test Condition	Test Method ISO	Units	Short carbon fiber reinforced PPS
				CF10%, Flame retardant
				A630T-10V
				>PPS-CF10<
Physical property				
Content of filler		-	wt%	10
Water Absorption	23℃×50%RH in water		%	-
Density	23℃	ISO1183	kg/m ³	1376
Mechanical property				
Tensile strength	23℃	ISO527-1,2	MPa	157
Elongation at Break	23℃	ISO527-1,2	%	1.4
Flexural Strength	23℃	ISO178	MPa	232
Flexural Modulus	23℃	ISO178	GPa	10.9
Coefficient of friction	Vs S45C、1MPa、0.33m/s	Suzuki Method	-	0.2
Coefficient of friction	Vs SUS、1MPa、0.33m/s	Suzuki Method	-	0.04
Amount of wear	Vs S45C、1MPa、0.33m/s	Suzuki Method	mg/h	3.3
Amount of wear	Vs SUS、1MPa、0.33m/s	Suzuki Method	mg/h	1.5
Limit of PV	Vs S45C	Suzuki Method	Mpa · m/s	0.9
Limit of PV	Vs SUS	Suzuki Method	Mpa · m/s	0.7
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	5.2
Heat property				
Melting Point		DSC Method	℃	278
Coef of Linear Thermal Expansion		ISO11359-2	×10 ⁻⁵ /℃	3.2
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	℃	260
Flammability		UL94	rank/thickness mmt	V-0
Electrical property				
Volume Resistivity		IEC60093	Ω · m	10 ¹
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	0.2
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	0.8

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

COPYRIGHT © TORAY INDUSTRIES,INC

