

Property	Test Condition	Test Method ISO	Units	Unreinforced
				High flow
				1401X45
				>PBT<
Physical property				
Water Absorption	24hrs. in 23°C water	ISO 62	%	0.08
Density	23°C	ISO 1183	kg/m ³	1310
Mechanical property				
Tensile strength	23°C	ISO 527-1,2	MPa	60
Elongation at Break	23°C	ISO 527-1,2	%	55
Tensile Modulus	23°C	ISO 527-1,2	GPa	-
Flexural Strength	23°C	ISO 178	MPa	87
Flexural Modulus	23°C	ISO 178	GPa	2.5
Coefficient of friction (Without lubrication)	Vs metal	Suzuki Method	-	-
Coefficient of friction	Vs metal	-	-	-
Rockwell Hardness	23°C	ISO 2039-2	R Scale	M77
Charpy Impact Strength (V-notched)	23°C	ISO 179	kJ/m ²	4.6
Charpy Impact Strength (Unnotched)	23°C	ISO 179	kJ/m ²	-
Heat property				
Coef of Linear Thermal Expansion	-30~100°C	ISO 11359-2	×10 ⁻⁵ /°C	11
Heat Deflection Temp Low Load	0.45MPa	ISO 75-1,2	°C	150
Heat Deflection Temp High Load	1.82MPa	ISO 75-1,2	°C	60
Flammability		UL94	rank/thickness m mt	HB (1/32")
Electrical property				
Volume Resistivity		IEC 60093	Ω · m	8×10 ¹⁴
Dielectric Strength		IEC 60243-1	MV/m	17
Dielectric Constant	23°C、60% RH、50Hz	IEC 60250	-	3.3
Dielectric Constant	23°C、60% RH、1MHz	IEC 60250	-	3.3
Dissipation Factor	23°C、60% RH、50Hz	IEC 60250	-	0.0020
Dissipation Factor	23°C、60% RH、1MHz	IEC 60250	-	0.02
Arc resistance	W electrode	IEC 60950	sec	144
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	2.2
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	2.4
Bar Flow	250°C,93MPa,1mmt	Toray Method	×10 ⁻³ m	-

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

