

Toraycon™ 6107G X01

PC+PBT

TECHNICAL DATA

Product Description

Alkali resistance, GF30%

Uses • Automotive Applications • Automotive Electronics • Valves/Valve Parts

Processing Method • Injection Molding

ISO Designation • >PBT+PC-I-GF30<

Type • PBT/Reinforced

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.46	g/cm ³	ISO 1183
Molding Shrinkage ¹			Internal Method
Across Flow : 3.00 mm	0.90	%	
Flow : 3.00 mm	0.40	%	
Water Absorption ² (24 hr, 23°C)	0.070	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	120	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	3.4	%	ISO 527-2
Flexural Modulus (23°C)	8000	MPa	ISO 178
Flexural Stress (23°C)	190	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	16.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, Unannealed	220	°C	ISO 75-2/B
1.8 MPa, Unannealed	202	°C	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating ³ (Equivalent)	HB		Internal Method

Notes

¹ 80x80x3mm

² in water

³ UL94

Toray Industries, Inc.

