

Torelina™ A515

PPS

TECHNICAL DATA

Product Description

Low wear and friction (PTFE+GF30%)

Uses

- Automotive Applications
- Power/Other Tools
- Printer
- Valves/Valve Parts

Processing Method

- Injection Molding

ISO Designation

- >PPS+PTFE-GF30<

Type

- PPS/Special purpose

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.68	g/cm ³	ISO 1183
Spiral Flow ¹	170	mm	Internal Method
Molding Shrinkage ²			Internal Method
Across Flow : 3.00 mm	0.85	%	
Flow : 3.00 mm	0.20	%	
Water Absorption ³ (24 hr, 23°C)	0.020	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	145	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	1.6	%	ISO 527-2
Flexural Modulus (23°C)	12000	MPa	ISO 178
Flexural Stress (23°C)	220	MPa	ISO 178
Shear Strength (23°C)	60	MPa	JIS K7214
Taber Abrasion Resistance (1000 Cycles)	50	mg	ISO 9352
Coefficient of Friction - vs. Metal	0.15		
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10.0	kJ/m ²	ISO 179
Charpy Unnotched Impact Strength (23°C)	35.0	kJ/m ²	ISO 179
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	> 260	°C	ISO 75-2/A
Melting Temperature	278	°C	ISO 11357-3
CLTE			ISO 11359-2
Flow	2.4	cm ³ /cm/°C	
Transverse	3.5	cm ³ /cm/°C	
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·m	IEC 60093
Electric Strength	26	kV/mm	IEC 60243-1
Dielectric Constant (23°C, 1 MHz)	3.4		IEC 60250
Dissipation Factor (23°C, 1 MHz)	0.002		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.74 mm)	V-0		UL 94



Toray Industries, Inc.

塑料专家 www.ponci.com.cn/wxb/ +13538586433 +18816996168

