

Property	Test Condition	Test Method ISO	Units	GF reinforced
				GF40%、Low chlorine
				A604-L02
				>PPS-GF40<
Physical property				
Water Absorption	24hrs. in 23℃ water	ISO62	%	0.02
Density	23℃	ISO1183	kg/m ³	1660
Color				Natural/Black
Mechanical property				
Tensile strength	23℃	ISO527-1,2	MPa	190
Elongation at Break	23℃	ISO527-1,2	%	1.6
Flexural Strength	23℃	ISO178	MPa	280
Flexural Modulus	23℃	ISO178	GPa	14.5
Charpy Impact Strength (V-notched)	23℃	ISO179	kJ/m ²	9.5
Charpy Impact Strength (Unnotched)	23℃	ISO179	kJ/m ²	55
Heat property				
Melting Point		ISO11357-3	℃	
Coef of Linear Thermal Expansion	Machine Direction	ISO11359-2	×10 ⁻⁵ /K	2.3
Coef of Linear Thermal Expansion	Transverse Direction	ISO11359-2	×10 ⁻⁵ /K	3.5
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	℃	260
Flammability		UL94	rank/thickness m mt	V-0 (0.20mmt)
Electrical property				
Volume Resistivity		IEC60093	Ω · m	10 ¹⁴
Dissipation Factor	23℃、60% RH、1MHz	IEC 60250	-	
Molding property				
Mold shrinkage(Machine Direction)	80×80×3mmt	Toray Method	%	0.2
Mold shrinkage(Transverse Direction)	80×80×3mmt	Toray Method	%	0.8
Bar Flow	320℃,98MPa,1mmt	Toray Method	×10 ⁻³ m	130

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

COPYRIGHT © TORAY INDUSTRIES,INC

