

Toyolac™ 250 X10 U ABS

TECHNICAL DATA

Product Description

High flow, High rigidity

Uses

- Camera Applications
- Computer Components
- Furniture
- Industrial Applications
- Kitchenware
- Television Housings
- Toys
- White Goods & Small Appliances

Processing Method

- Injection Molding

ISO Designation

- >ABS<

Type

- ABS/Standard

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.05	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	48	g/10 min	ISO 1133
Molding Shrinkage ¹	0.40 to 0.60	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	57	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	16	%	ISO 527-2
Flexural Modulus (23°C)	2580	MPa	ISO 178
Flexural Stress (23°C)	83	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	10.0	kJ/m²	ISO 179
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	115		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	83	°C	ISO 75-2/A
Vicat Softening Temperature	95	°C	
CLTE - Flow	7.0	cm⁻⁵/cm/°C	ASTM D696
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm)	HB		UL 94

Notes

¹ 23°C/50%RH

Toray Industries, Inc.

