

Toyolac™ 950 X02 U MABS

TECHNICAL DATA

Product Description

High chemical resistant

Uses	- Automotive Interior Parts - Cosmetics - Kitchenware - Kitchenware - White Goods & Small Appliances
Appearance	Clear/Transparent
Processing Method	- Extrusion - Film Extrusion - Injection Molding - Sheet Extrusion
ISO Designation	>MABS<
Type	ABS/Transparent

ASTM & ISO Properties

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.09	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	7.0	g/10 min	ISO 1133
Molding Shrinkage ¹	0.40 to 0.60	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	53	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	13	%	ISO 527-2
Flexural Modulus (23°C)	2340	MPa	ISO 178
Flexural Stress (23°C)	74	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	12.0	kJ/m²	ISO 179
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale, 23°C)	110		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	75	°C	ISO 75-2/A
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.5 mm)	HB		UL 94
Optical	Nominal Value	Unit	Test Method
Light Transmittance ² (Total)	86.0	%	ISO 13468
Haze ²	3.00	%	ISO 14782

Notes

¹ 23°C/50%RH

² 23°C/50%RH, 3mm thickness

Toray Industries, Inc.

