

PRODUCT CODE	TISARBON 40 D03 F02 R01
PRODUCT DESCRIPTION	PC, 40% REINFORCED, FLAME RETARDANT- HALOGEN FREE, NATURAL

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm ³	1.50-1.53
	MOLDING SHRINKAGE	PARALLEL	ISO 294-4	%	0.1-0.3
	MOISTURE CONTENT	-	ISO 15512	%	<0.2

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	110-120
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	>2
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	9500-10500
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	kJ/m ²	7-12

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	-
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	-
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	-
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	-
	BALL PRESSURE TEST	-	ISO 60695-10-2	-	-

PRODUCT CODE	TİSARBON 40 D03 F02 R01
PRODUCT DESCRIPTION	PC, 40% REINFORCED, FLAME RETARDANT- HALOGEN FREE, NATURAL

ELECTRICAL & FLAMMABILITY	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	V0
	FLAME RATING	1,6 mm	UL 94	-	V0
	GLOW WIRE FLAMMABILITY INDEX	2 mm	IEC 60695	°C	960
	GLOW WIRE IGNITABILITY TEMPERATURE	2 mm	IEC 60695	°C	-
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	-
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	10E+14
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	10E+14

INJECTION PROCESS	ÖZELLİKLERİ	BİRİM	DEĞER
	PREDRYING TEMPERATURE	°C	90-120
	PREDRYING TIME	Hours	3-4
	MELTING TEMPERATURE	°C	270-300
	NOZZLE TEMPERATURE	°C	280-290
	PRE- 3 REGION TEMPERATURE	°C	260-270
	MID-2 REGION TEMPERATURE	°C	280-290
	AFT-1 REGION TEMPERATURE	°C	280-290
	MOLD TEMPERATURE	°C	70-120
	HOLD PRESSURE	MPa	90-120