

PRODUCT CODE	TISBLEND FL 20D03 R01
PRODUCT DESCRIPTION	PBT/PET, %20 GLASS FIBER REINFORCED, NATURAL

PHYSICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	DENSITY	-	ISO 1183	g/cm ³	1.45-1.47
	MOLDING SHRINKAGE	PARALLEL	ISO 294-4	%	-
	MOISTURE CONTENT	-	ISO 15512	%	0,2

MECHANICAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	YIELD STRENGTH	+23°C	ISO 527-2	MPa	115-125
	TENSILE STRESS AT BREAK	+23°C	ISO 527-2	MPa	-
	TENSILE STRAIN AT BREAK	+23°C	ISO 527-2	%	-
	TENSILE MODULUS	+23°C	ISO 527-2	MPa	8000-9000
	IZOD IMPACT STRENGTH, NOTCHED	+23°C	ISO 180/A	kJ/m ²	5-6

THERMAL	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	VICAT SOFTENING TEMPERATURE	50 N	ISO 306	°C	-
	HEAT DEFLECTION TEMPERATURE	0,45 MPa	ISO 75	°C	-
	HEAT DEFLECTION TEMPERATURE	1,80 MPa	ISO 75	°C	210
	MELTING TEMPERATURE	10 K/min	ISO 11357	°C	225-255
	BALL PRESSURE TEST	120 °C	ISO 60695-10-2	-	-

PRODUCT CODE	TISBLEND FL 20D03 R01
PRODUCT DESCRIPTION	PBT/PET, %20 GLASS FIBER REINFORCED, NATURAL

ELECTRICAL&FLAMMABILITY	PROPERTIES	CONDITION	STANDARD	UNITS	VALUE
	FLAME RATING	0,75 mm	UL 94	-	HB
	FLAME RATING	1,6 mm	UL 94	-	HB
	GLOW WIRE FLAMMABILITY INDEX	2 mm	IEC 60695	°C	-
	GLOW WIRE IGNITABILITY TEMPERATURE	2 mm	IEC 60695	°C	-
	COMPARATIVE TRACKING INDEX	Solution A	ISO 60112	Volt	-
	VOLUME RESISTIVITY	-	IEC 60093	Ohm.cm	-
	SURFACE RESISTIVITY	-	IEC 60093	Ohm	-

INJECTION PROCESS	PROPERTIES	UNITS	VALUE
	PREDRYING TEMPERATURE	°C	80-120
	PREDRYING TIME	hours	3-4
	MELTING TEMPERATURE	°C	-
	NOZZLE TEMPERATURE	°C	270-280
	PRE- 3 REGION TEMPERATURE	°C	260-270
	MID-2 REGION TEMPERATURE	°C	260-270
	AFT-1 REGION TEMPERATURE	°C	260-270
	MOLD TEMPERATURE	°C	60-100